

LEXAN™ HP6 resin

Polycarbonate
SABIC Innovative Plastics

Message:
Low/med flow polycarbonate. For medical devices and pharmaceutical applications. Healthcare management of change, biocompatible (ISO10993 or USP Class VI). EtO and steam sterilizable. Contains mold release.

General Information			
UL YellowCard	E121562-220863		
Additive	Mold Release		
Features	Biocompatible		
	Ethylene Oxide Sterilizable		
	Medium Flow		
	Steam Sterilizable		
Uses	Medical/Healthcare Applications		
	Pharmaceuticals		
Agency Ratings	ISO 10993		
	USP Class VI		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.20	g/cm ³	ASTM D792, ISO 1183
--	1.19	g/cm ³	ASTM D792
Specific Volume	0.830	cm ³ /g	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	7.0	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR)			ISO 1133
220°C/5.0 kg	4.00	cm ³ /10min	
300°C/1.2 kg	6.00	cm ³ /10min	
Molding Shrinkage - Flow (3.20 mm)	0.50 to 0.70	%	Internal Method
Water Absorption			
24 hr	0.15	%	ASTM D570
Saturation, 23°C	0.35	%	ISO 62
Equilibrium, 23°C	0.35	%	ASTM D570
Equilibrium, 100°C	0.58	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.15	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785

M-Scale	70		
R-Scale	118		
Ball Indentation Hardness (H 358/30)	95.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2310	MPa	ASTM D638
--	2350	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	62.0	MPa	ASTM D638
Yield	63.0	MPa	ISO 527-2/50
Break ³	68.0	MPa	ASTM D638
Break	70.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	7.0	%	ASTM D638
Yield	6.0	%	ISO 527-2/50
Break ⁵	140	%	ASTM D638
Break	120	%	ISO 527-2/50
Flexural Modulus			
50.0 mm Span ⁶	2340	MPa	ASTM D790
-- ⁷	2300	MPa	ISO 178
Flexural Stress			
--	90.0	MPa	ISO 178
Yield, 50.0 mm Span ⁸	97.0	MPa	ASTM D790
Taber Abrasion Resistance			
1000 Cycles, 1000 g, CS-17 Wheel	10.0	mg	Internal Method
1000 Cycles, 1000 g, CS-17 Wheel	10.0	mg	ASTM D1044
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			
23°C ⁹	95	kJ/m ²	ISO 179/1eA
23°C	35	kJ/m ²	ISO 179/2C
Notched Izod Impact			
-30°C	140	J/m	ASTM D256
23°C	910	J/m	ASTM D256
-30°C ¹⁰	10	kJ/m ²	ISO 180/1A
23°C ¹¹	65	kJ/m ²	ISO 180/1A
Unnotched Izod Impact (23°C)	3200	J/m	ASTM D4812
Instrumented Dart Impact (23°C, Total Energy)	65.0	J	ASTM D3763
Gardner Impact (23°C)	169	J	ASTM D3029
Tensile Impact Strength ¹²	630	kJ/m ²	ASTM D1822
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			

0.45 MPa, Unannealed, 6.40 mm	137	°C	ASTM D648
0.45 MPa, Unannealed, 100 mm Span ¹³	138	°C	ISO 75-2/Be
1.8 MPa, Unannealed, 6.40 mm	132	°C	ASTM D648
1.8 MPa, Unannealed, 100 mm Span ¹⁴	127	°C	ISO 75-2/Ae
1.8 MPa, Unannealed, 64.0 mm Span ¹⁵	124	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	154	°C	ASTM D1525 ¹⁶
--	144	°C	ISO 306/B50
--	145	°C	ISO 306/B120
Ball Pressure Test			IEC 60695-10-2
125°C	Pass		
140°C ¹⁷	Pass		
CLTE			
Flow : -40 to 40°C	6.2E-5	cm/cm/°C	ASTM E831
Flow : -40 to 40°C	6.0E-5	cm/cm/°C	ISO 11359-2
Flow : 23 to 80°C	7.0E-5	cm/cm/°C	ISO 11359-2
Transverse : -40 to 40°C	5.7E-5	cm/cm/°C	ASTM E831
Transverse : -40 to 40°C	6.0E-5	cm/cm/°C	ISO 11359-2
Specific Heat	1250	J/kg/°C	ASTM C351
Thermal Conductivity			
--	0.19	W/m/K	ASTM C177
--	0.20	W/m/K	ISO 8302
RTI Elec	130	°C	UL 746
RTI Imp	130	°C	UL 746
RTI Str	130	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+17	ohms·cm	ASTM D257
Dielectric Strength			
3.20 mm, in Air	15	kV/mm	ASTM D149
3.20 mm, in Oil	17	kV/mm	IEC 60243-1
Dielectric Constant			
50 Hz	3.17		ASTM D150
60 Hz	3.17		ASTM D150
1 MHz	2.96		ASTM D150
50 Hz	2.70		IEC 60250
60 Hz	2.70		IEC 60250
1 MHz	2.70		IEC 60250
Dissipation Factor			
50 Hz	9.0E-4		ASTM D150
60 Hz	9.0E-4		ASTM D150
1 MHz	0.010		ASTM D150, IEC 60250
50 Hz	1.0E-3		IEC 60250

60 Hz	1.0E-3		IEC 60250
Comparative Tracking Index (CTI)	PLC 2		UL 746
High Amp Arc Ignition (HAI)	PLC 1		UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 2		UL 746
Hot-wire Ignition (HWI)	PLC 2		UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.47 mm)	HB		UL 94
Glow Wire Flammability Index (1.00 mm)	850	°C	IEC 60695-2-12
Oxygen Index	25	%	ISO 4589-2
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.586		ASTM D542, ISO 489
Transmittance (2540 μm)	88.0	%	ASTM D1003
Haze (2540 μm)	1.0	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	3.0 to 4.0	hr	
Drying Time, Maximum	48	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 to 60	%	
Rear Temperature	288 to 310	°C	
Middle Temperature	299 to 321	°C	
Front Temperature	310 to 332	°C	
Nozzle Temperature	304 to 327	°C	
Processing (Melt) Temp	310 to 332	°C	
Mold Temperature	82.2 to 116	°C	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	40 to 70	rpm	
Vent Depth	0.025 to 0.076	mm	
NOTE			
1.	5.0 mm/min		
2.	Type I, 50 mm/min		
3.	Type I, 50 mm/min		
4.	Type I, 50 mm/min		
5.	Type I, 50 mm/min		
6.	1.3 mm/min		
7.	2.0 mm/min		
8.	1.3 mm/min		
9.	80*10*4 sp=62mm		
10.	80*10*4		
11.	80*10*4		
12.	Type S		
13.	120*10*4 mm		

14.	120*10*4 mm
15.	80*10*4 mm
16.	Rate B (120°C/h), Loading 2 (50 N)
17.	Approximate maximum

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

