

XANTAR® LDS 3724

Polycarbonate + ABS

Mitsubishi Engineering-Plastics Corp

Message:

Laser Direct Structuring (LDS)*, Improved Impact

*The compound is intended specifically for the use in the process of manufacturing conducting path designed according to the German application of the patent 101 32 092 of LPKF Laser & Electronics AG. Please address straight to LPKF Laser & Electronics AG (www.LPKF.de).

General Information			
UL YellowCard	E340159-101357462		
Features	Good Impact Resistance		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.23	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	14	g/10 min	ISO 1133
Molding Shrinkage - Flow	0.60	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2250	MPa	ISO 527-2
Tensile Stress (Yield)	49.0	MPa	ISO 527-2
Tensile Strain (Yield)	4.0	%	ISO 527-2
Nominal Tensile Strain at Break	> 50	%	ISO 527-2
Flexural Modulus	2200	MPa	ISO 178
Flexural Stress	77.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	No Break		
23°C	No Break		
Notched Izod Impact Strength			ISO 180/4A
-20°C	40	kJ/m ²	
23°C	55	kJ/m ²	
Multi-Axial Instrumented Impact Energy			
-20°C ¹	20.0	J	Internal Method
23°C	35.0	J	ISO 6603-2
23°C ²	25.0	J	Internal Method
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	100	°C	ISO 75-2/A
Vicat Softening Temperature	122	°C	ISO 306/B50
CLTE			ISO 11359-2
Flow	7.0E-5	cm/cm/°C	
Transverse	7.0E-5	cm/cm/°C	

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Relative Permittivity (1.00 GHz)	3.00		IEC 60250
Dissipation Factor (1.00 GHz)	6.0E-3		IEC 60250
Flammability	Nominal Value	Unit	Test Method
Flammability Classification (0.800 mm)	HB		IEC 60695-11-10, -20
NOTE			
1.	Part with rib, Based on ISO 6603-2		
2.	Part with rib, Based on ISO 6603-2		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

