

VENYL SN000 - 3121

Polyamide 6
AD majoris

Message:

VENYL SN000 - 3121 is a standard coloured polyamide 6 intended for Injection moulding.

APPLICATIONS

VENYL SN000 - 3121 has been developed especially for very demanding applications in automotive industry and electrical parts.

Products requiring excellent combination between thermal and mechanical properties.

VENYL SN000 - 3121 is available in both yellow (VENYL SN000 - 3121) but other colours can be provided on request.

General Information				
Features		Recyclable Material		
Uses	Automotive Applications			
	Electrical Parts			
Appearance	Colors Available			
	Yellow			
Forms		Pellets		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.14	--	g/cm ³	ISO 1183
Molding Shrinkage	0.50 to 1.5	--	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	2.8 to 3.0	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (L-Scale)	100	--		ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	3100	1100	MPa	ISO 527-2
Tensile Stress (Break)	85.0	65.0	MPa	ISO 527-2
Tensile Strain (Break)	50	200	%	ISO 527-2
Flexural Modulus	2700	900	MPa	ISO 178
Flexural Stress	130	65.0	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	5.0	40	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	No Break	No Break		ISO 179
Notched Izod Impact	50	150	J/m	ISO 180
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				

0.45 MPa, Unannealed	170	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	80.0	--	°C	ISO 75-2/A
Melting Temperature (DSC)	220	--	°C	ISO 3146
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+12	1.0E+10	ohms	DIN 53482
Volume Resistivity	1.0E+15	1.0E+12	ohms·cm	DIN 53482
Comparative Tracking Index (Solution A)	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.60 mm)	V-2	--		UL 94
Glow Wire Flammability Index (2.00 mm)	750	--	°C	IEC 60695-2-12
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	4.0		hr	
Rear Temperature	250 to 270		°C	
Middle Temperature	240 to 255		°C	
Front Temperature	240 to 255		°C	
Nozzle Temperature	220 to 265		°C	
Mold Temperature	50.0 to 70.0		°C	
Injection Pressure	70.0 to 90.0		MPa	
Injection Rate	Fast			
Holding Pressure	35.0 to 60.0		MPa	
Screw L/D Ratio	15.0:1.0 to 20.0:1.0			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT