

Hostacom G3 N01 L

Polypropylene Homopolymer

LyondellBasell Industries

Message:

"Hostacom" G3 N01 L is a 30% glass coupled PP homopolymer with low flow, very high stiffness and low CLTE. Low creep under load at elevated temperatures. The grade is not intended for medical, pharmaceutical or drinking water applications

General Information			
UL YellowCard	E31765-230620		
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Good Creep Resistance		
	Good Stiffness		
	Homopolymer		
	Low Flow		
Uses	Automotive Applications		
	Automotive Under the Hood		
	Structural Parts		
Agency Ratings	UL 94		
Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR)			ISO 1133
230°C/2.16 kg	1.00	cm ³ /10min	
230°C/5.0 kg	5.00	cm ³ /10min	
Molding Shrinkage	0.30 to 1.0	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	110	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus - Secant	6500	MPa	ISO 527-2
Tensile Stress (Break)	85.0	MPa	ISO 527-2/50
Tensile Strain (Break)	3.0	%	ISO 527-2/50
Flexural Modulus - Secant	5500	MPa	ISO 178
Flexural Stress	120	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-20°C	7.0	kJ/m ²	
23°C	9.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-20°C	38	kJ/m ²	

23°C	40	kJ/m ²	
Notched Izod Impact Strength (23°C)	6.0	kJ/m ²	DIN 53453
Unnotched Izod Impact Strength (23°C)	22	kJ/m ²	DIN 53453
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	155	°C	ISO 75-2/B
1.8 MPa, Unannealed	140	°C	ISO 75-2/A
Vicat Softening Temperature			
--	160	°C	ISO 306/A50
--	130	°C	ISO 306/B50
RTI Elec	65.0	°C	UL 746
RTI Imp	65.0	°C	UL 746
RTI Str	65.0	°C	UL 746
Flammability	Nominal Value	Test Method	
Flame Rating	HB	UL 94	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

