

Wondel® P PG8

Polypropylene

Nanjing Julong Engineering Plastics Co., LTD

Message:

Wondel® P PG8 is a Polypropylene material filled with 40% glass fiber. It is available in Asia Pacific. Primary attribute of Wondel® P PG8: Flame Rated.
Typical application of Wondel® P PG8: Automotive

General Information			
UL YellowCard	E211125-102028906		
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.23	g/cm ³	ISO 1183
Molding Shrinkage	0.40 to 0.70	%	ISO 294-4
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	106		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	90.0	MPa	ISO 527-2
Tensile Strain (Break)	3.0	%	ISO 527-2
Flexural Stress	130	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	13	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	155	°C	ISO 75-2/B
Melting Temperature (DSC)	167	°C	ISO 3146
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT