Stirol UPS-0801 (1s.)

High Impact Polystyrene JSC CONCERN STIROL

Message:

UPS-0801 is for manufacturing of goods and package for contact with foodstuffs.

General Information			
Features	Food Contact Acceptable		
	High Impact Resistance		
	- 10.1		
Uses	Food Packaging		
Forms	Granules		
Processing Method	Die Molding		
	Extrusion		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR)	2.0 to 4.5	g/10 min	ISO 1133
Water Absorption (Equilibrium, 23°C, 50%			
RH)	< 0.10	%	ISO 62
Bound Styrene	< 0.1	%	
Purity ¹	10.0		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strain (Break)	> 30	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	6.6 to 7.5	kJ/m²	ISO 179
NOTE			
	Disc surface should be clean. It is allowed one insertion with diameter 0,2-0,3 mm at the surfaces of disks converting to		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

area, cm²

Tel: +86 21 5895 8519

1.

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

