

Hifax CB259

Thermoplastic Polyolefin Elastomer

LyondellBasell Industries

Message:

Hifax CB259 medium high melt flow, 1,600 MPa flexural modulus, low CLTE, paintable, mineral-filled thermoplastic elastomeric olefin (TEO) resin has a very good balance of impact resistance, rigidity and dimensional stability. It was designed for exterior ornamentation applications requiring stiffness and low thermal expansion characteristics.

General Information			
Filler / Reinforcement	Mineral		
Features	Good Dimensional Stability		
	Good Impact Resistance		
	High Rigidity		
	Low Shrinkage		
	Medium Flow		
	Paintable		
Uses	Automotive Applications		
	Automotive Exterior Parts		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.10	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	13	g/10 min	ASTM D1238, ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	18.0	MPa	ISO 527-2
Tensile Strain			
Yield	8.0	%	ISO 527-2
Break, 23°C	400	%	ISO 527-2/50
Flexural Modulus	1600	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180
-40°C	3.0	kJ/m ²	
23°C	33	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	94.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	53.0	°C	ISO 75-2/A
CLTE - Flow (-30 to 100°C)	4.9E-5	cm/cm/°C	ASTM E228, ISO 11359-2

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

