

Kingfa HR-527B

Acrylonitrile Butadiene Styrene

Kingfa

Message:

Kingfa HR-527B is an acrylonitrile butadiene styrene (ABS) material. This product is available in North America or Asia Pacific region. The processing method is injection molding.

The main features of Kingfa HR-527B are:

flame retardant/rated flame

Heat resistance

The typical application field of Kingfa HR-527B is: automotive industry

General Information			
Features	Heat resistance, high		
Uses	Car interior parts		
	Car interior equipment		
	Automotive exterior parts		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.06	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	6.5	g/10 min	ASTM D1238
Molding Shrinkage - Flow (23°C)	0.30 - 0.60	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	110		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	48.0	MPa	ASTM D638
Tensile Elongation ² (Break)	20	%	ASTM D638
Flexural Modulus ³	2600	MPa	ASTM D790
Flexural Strength ⁴	72.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
23°C, 3.20 mm	170	J/m	ASTM D256
23°C, 6.40 mm	140	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, 6.40mm	110	°C	ASTM D648
1.8 MPa, unannealed, 6.40mm	101	°C	ASTM D648
Vicat Softening Temperature			
--	118	°C	ASTM D1525 ⁵
--	110	°C	ASTM D1525 ⁶

Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength	23	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm	HB		UL 94
3.20 mm	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	90.0 - 100	°C	
Drying Time	2.0 - 4.0	hr	
Rear Temperature	190 - 220	°C	
Middle Temperature	210 - 240	°C	
Front Temperature	220 - 245	°C	
Processing (Melt) Temp	220 - 250	°C	
Mold Temperature	30.0 - 80.0	°C	
Injection Rate	Slow-Moderate		
Back Pressure	0.00 - 0.0100	MPa	
Injection instructions			
Processing Temperature Limit: 270°C			
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	2.0 mm/min		
4.	2.0 mm/min		
5.	标准 B (120°C/h), 压力1 (10N)		
6.	速率 A (50°C/h), 载荷2 (50N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

