

RONFALIN® C C130 GF10

Polycarbonate + ABS

A. Schulman Europe

Message:

RONFALIN® C C130 GF10 is a Polycarbonate + ABS (PC+ABS) material filled with 10% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Primary attribute of RONFALIN® C C130 GF10: Flame Rated.

Typical application of RONFALIN® C C130 GF10: Engineering/Industrial Parts

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Uses	Machine/Mechanical Parts		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	25	g/10 min	ISO 1133
Molding Shrinkage	0.30 to 0.50	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3800	MPa	ISO 527-2
Tensile Stress (Yield)	65.0	MPa	ISO 527-2
Flexural Modulus	3650	MPa	ISO 178
Flexural Stress	95.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area) (23°C)	10.0	kJ/m ²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	131	°C	ISO 75-2/B
1.8 MPa, Unannealed	114	°C	ISO 75-2/A
Vicat Softening Temperature	130	°C	ISO 306/B50
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT