

LNP™ LUBRICOMP™ WCL36 compound

Polybutylene Terephthalate

SABIC Innovative Plastics

Message:

LNP LUBRICOMP WCL36 is a compound based on PBT resin containing 30% Carbon Fiber, 15% PTFE. Added features of this grade include: Electrically Conductive, Wear Resistant.

Also known as: LNP* LUBRICOMP* Compound WCL-4036

Product reorder name: WCL36

General Information			
Filler / Reinforcement	Carbon Fiber,30% Filler by Weight		
Additive	PTFE Lubricant (15%)		
Features	Electrically Conductive		
	Good Wear Resistance		
	Lubricated		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.51	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			ASTM D955
Flow : 24 hr	0.20 to 0.40	%	
Across Flow : 24 hr	1.0 to 3.0	%	
Water Absorption			
24 hr, 50% RH	0.030	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.050	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	23400	MPa	ASTM D638
--	20600	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	125	MPa	ASTM D638
Yield	130	MPa	ISO 527-2/5
Break ³	125	MPa	ASTM D638
Break	121	MPa	ISO 527-2/5
Tensile Elongation			
Yield ⁴	1.0	%	ASTM D638
Yield	1.0	%	ISO 527-2/5
Break ⁵	1.0	%	ASTM D638
Break	1.0	%	ISO 527-2/5
Flexural Modulus			
50.0 mm Span ⁶	14900	MPa	ASTM D790

-- ⁷	18100	MPa	ISO 178
Flexural Stress			
--	187	MPa	ISO 178
Yield, 50.0 mm Span ⁸	173	MPa	ASTM D790
Break, 50.0 mm Span ⁹	175	MPa	ASTM D790
Coefficient of Friction			ASTM D3702 Modified
vs. Itself - Dynamic	0.35		
vs. Itself - Static	0.31		
Wear Factor			ASTM D3702 Modified
Ring	2.50 to 3.00	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	
Washer	25.0	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	37	J/m	ASTM D256
23°C ¹⁰	3.5	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	390	J/m	ASTM D4812
23°C ¹¹	24	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Total Energy	6.70	J	ASTM D3763
--	1.40	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	222	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ¹²	223	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	210	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ¹³	210	°C	ISO 75-2/Af
CLTE			ASTM D696
Flow : -30 to 30°C	1.3E-5	cm/cm/°C	
Transverse : -30 to 30°C	3.6E-5	cm/cm/°C	
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.050	%	
Rear Temperature	221 to 232	°C	
Middle Temperature	243 to 254	°C	
Front Temperature	260 to 271	°C	
Processing (Melt) Temp	238 to 266	°C	
Mold Temperature	82.2 to 98.9	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			

1.	50 mm/min
2.	Type I, 5.0 mm/min
3.	Type I, 5.0 mm/min
4.	Type I, 5.0 mm/min
5.	Type I, 5.0 mm/min
6.	1.3 mm/min
7.	2.0 mm/min
8.	1.3 mm/min
9.	1.3 mm/min
10.	80*10*4
11.	80*10*4
12.	80*10*4 mm
13.	80*10*4 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

