

ALAMID® 6 GK 50

Polyamide 6

LEIS Polytechnik - polymere Werkstoffe GmbH

Message:

polyamide 6 + 50% glass beads, stabilized

General Information			
Filler / Reinforcement	Glass Bead,50% Filler by Weight		
Additive	Unspecified Stabilizer		
Physical	Nominal Value	Unit	Test Method
Density	1.56	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6300	MPa	ISO 527-2
Tensile Stress (Yield)	85.0	MPa	ISO 527-2
Tensile Strain (Break)	> 5.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength	35	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Melting Temperature (DSC) ¹	221	°C	ISO 3146
NOTE			
1.	10K/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

