

Sorona® 3030GV NC010

RENEWABLY SOURCED™ THERMOPLASTIC POLYMER*

DuPont Performance Polymers

Message:

30% Glass Reinforced, Renewably Sourced, Polytrimethylene Terephthalate

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Mold Release		
Agency Ratings	UL Unspecified Rating		
Forms	Pellets		
Processing Method	Injection Molding		
Multi-Point Data	Isothermal Stress vs. Strain (ISO 11403-1)		
	Secant Modulus vs. Strain (ISO 11403-1)		
Part Marking Code (ISO 11469)	>PTT-GF30<		
Resin ID (ISO 1043)	PTT-GF30		
Physical	Nominal Value	Unit	Test Method
Density	1.56	g/cm³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	0.70	%	
Flow	0.20	%	
Water Absorption (24 hr)	0.080	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	11000	MPa	ISO 527-2
Tensile Stress (Break)	165	MPa	ISO 527-2
Tensile Strain (Break)	2.5	%	ISO 527-2
Flexural Modulus	9600	MPa	ISO 178
Flexural Stress	245	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	9.0	kJ/m²	
23°C	9.0	kJ/m²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	45	kJ/m²	
23°C	50	kJ/m²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	226	°C	ISO 75-2/B
1.8 MPa, Unannealed	210	°C	ISO 75-2/A

Melting Temperature ¹	227	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow	7.0E-6	cm/cm/°C	
Transverse	8.3E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	8.0E+13	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Electric Strength	38	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	4.20		
1 MHz	4.00		
Dissipation Factor			IEC 60250
100 Hz	1.2E-3		
1 MHz	0.016		
Comparative Tracking Index	300	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flammability Classification			IEC 60695-11-10, -20
0.750 mm	HB		
1.50 mm	HB		
Oxygen Index	20	%	ISO 4589-2
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

