

Softflex® 2910

Thermoplastic Elastomer

Network Polymers, Inc.

Message:

Softflex® 2910 is a Thermoplastic Elastomer (TPE) product. It is available in North America. Typical application: Engineering/Industrial Parts.

General Information			
Uses	Overmolding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.03	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) ¹ (200°C/5.0 kg)	0.30	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow : 3.18 mm	0.80	%	
Across Flow : 3.18 mm	0.80	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A	91		
Shore A, 10 sec	85		
Mechanical	Nominal Value	Unit	Test Method
Taber Abrasion Resistance (1000 Cycles, 1000 g, H-22 Wheel)	241	mg	ASTM D3389
Films	Nominal Value	Unit	Test Method
Peel Strength - 90°	1.1	kN/m	ASTM D429
Overmold Bonding	ABS, PC, ABS/PC, PPO		
Elastomers	Nominal Value	Unit	Test Method
Tensile Set (100% Strain)	4	%	ASTM D412
Tensile Stress			ASTM D412
50% Strain	1.50	MPa	
100% Strain	1.99	MPa	
300% Strain	3.36	MPa	
Tensile Strength ² (Yield)	11.3	MPa	ASTM D412
Tensile Elongation (Break)	870	%	ASTM D412
Tear Strength	44.8	kN/m	ASTM D624
Compression Set			ASTM D395B
23°C, 22 hr	39	%	
70°C, 22 hr	96	%	
100°C, 22 hr	98	%	
Impact	Nominal Value	Unit	Test Method
Gardner Impact (23°C)	31.6	J	ASTM D5420
NOTE			

1.	Procedure A
2.	510 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

