

PRL PC-UV4-(color)-1

Polycarbonate

Polymer Resources Ltd.

Message:

PRL PC-UV4-(color)-1 is a Polycarbonate (PC) product. It can be processed by injection molding and is available in North America.

Characteristics include:

RoHS Compliant

Good Mold Release

Good UV Resistance

Mold Release Agent

UV Stabilized

General Information			
Additive	Mold Release		
	UV Stabilizer		
Features	Good Flow		
	Good Mold Release		
	Good UV Resistance		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	18 to 30	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow : 3.18 mm	0.50 to 0.70	%	
Across Flow : 3.18 mm	0.50 to 0.70	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	70		
R-Scale	118		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, 3.18 mm	62.1	MPa	
Break, 3.18 mm	65.5	MPa	
Tensile Elongation			ASTM D638
Yield, 3.18 mm	6.0	%	
Break, 3.18 mm	120	%	
Flexural Modulus (3.18 mm)	2280	MPa	ASTM D790
Flexural Strength (3.18 mm)	92.4	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	640	J/m	ASTM D256
Gardner Impact (3.18 mm)	> 36.2	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.18 mm	129	°C	
1.8 MPa, Unannealed, 3.18 mm	124	°C	
Vicat Softening Temperature	141	°C	ASTM D1525 ¹
Optical	Nominal Value	Unit	Test Method
Transmittance (2540 μm)	88.0	%	ASTM D1003
Haze (2540 μm)	1.0	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	118 to 124	°C	
Drying Time	3.0 to 4.0	hr	
Drying Time, Maximum	8.0	hr	
Rear Temperature	249 to 271	°C	
Middle Temperature	260 to 282	°C	
Front Temperature	271 to 293	°C	
Processing (Melt) Temp	266 to 293	°C	
Mold Temperature	65.6 to 93.3	°C	
NOTE			

1. Rate B (120°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

