

# TEREZ PA 6.6 7600 UV

Polyamide 66  
TER HELL PLASTIC GMBH

Message:

Medium viscosity Polyamide 6.6 with good flowability, good impact resistance, bright natural colour and UV-stabilizer.  
For long flow distances, short moulding cycles with good demoldability.

General Information			
Additive	UV Stabilizer		
Features	Fast Molding Cycle		
	Good Dimensional Stability		
	Good Flow		
	Good Impact Resistance		
	Medium Viscosity		
Appearance	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm <sup>3</sup>	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3600	MPa	ISO 527-2
Tensile Strain (Yield)	4.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.0	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	230	°C	ISO 75-2/B
1.8 MPa, Unannealed	85.0	°C	ISO 75-2/A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT