

LEXAN™ LGK5030 resin

Polycarbonate

SABIC Innovative Plastics Asia Pacific

Message:

Glass reinforced. Flame retardant.

General Information			
UL YellowCard	E45587-236912	E207780-228441	
Filler / Reinforcement	Glass Fiber		
Additive	Flame Retardant		
Features	Flame Retardant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.61	g/cm³	ASTM D792
Molding Shrinkage			Internal Method
Flow : 3.20 mm	0.050 to 0.25	%	
Across Flow : 3.20 mm	0.10 to 0.30	%	
Water Absorption (24 hr)	0.14	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Break)	142	MPa	ASTM D638
Tensile Elongation ² (Break)	4.0	%	ASTM D638
Flexural Modulus ³ (50.0 mm Span)	10700	MPa	ASTM D790
Flexural Strength ⁴ (Break, 50.0 mm Span)	187	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	120	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.40 mm)	144	°C	ASTM D648
CLTE			ASTM D696
Flow : -30 to 30°C	2.2E-5	cm/cm/°C	
Transverse : -30 to 30°C	4.0E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength (3.20 mm, in Oil)	16	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.47 mm	V-1		
2.79 mm	V-0		
3.61 mm	5VA		
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	

Drying Time	3.0 to 4.0	hr
Drying Time, Maximum	48	hr
Suggested Max Moisture	0.020	%
Suggested Shot Size	40 to 60	%
Rear Temperature	293 to 316	°C
Middle Temperature	304 to 327	°C
Front Temperature	316 to 338	°C
Nozzle Temperature	310 to 332	°C
Processing (Melt) Temp	316 to 338	°C
Mold Temperature	82.2 to 116	°C
Back Pressure	0.345 to 0.689	MPa
Screw Speed	40 to 70	rpm
Vent Depth	0.025 to 0.076	mm

NOTE

- | | |
|----|-------------------|
| 1. | Type I, 50 mm/min |
| 2. | Type I, 50 mm/min |
| 3. | 1.3 mm/min |
| 4. | 1.3 mm/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

