

LNP™ THERMOCOMP™ UC008H compound

Polyphthalamide

SABIC Innovative Plastics

Message:

LNP THERMOCOMP UC008H is a compound based on Polyphthalamide resin containing Carbon Fiber. Added features of this material include: Electrically Conductive.

Also known as: LNP* THERMOCOMP* Compound UC-1008

Product reorder name: UC008H

General Information			
Filler / Reinforcement	Carbon fiber reinforced material		
Features	Conductivity		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.38	g/cm ³	ASTM D792
Molding Shrinkage			
Flow: 24 hours	0.70 - 0.90	%	ASTM D955
Transverse flow: 24 hours	0.70 - 0.90	%	ASTM D955
Vertical flow direction: 24 hours	0.70 - 0.90	%	ISO 294-4
Flow direction: 24 hours	0.70 - 0.90	%	ISO 294-4
Water Absorption			
24 hr, 50% RH	0.40	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.46 - 1.4	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	33800	MPa	ASTM D638
--	35500	MPa	ISO 527-2/1
Tensile Strength			
Fracture	261	MPa	ASTM D638
Fracture	232	MPa	ISO 527-2
Tensile Elongation			
Fracture	1.0	%	ASTM D638
Fracture	1.3	%	ISO 527-2
Flexural Modulus			
--	26800	MPa	ASTM D790
--	26600	MPa	ISO 178
Flexural Strength			
--	441	MPa	ASTM D790
--	425	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	59	J/m	ASTM D256

23°C ²	7.3	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	330	J/m	ASTM D4812
23°C ³	45	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	7.00	J	ASTM D3763
--	5.00	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, unannealed, 3.20mm	> 249	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ⁴	> 250	°C	ISO 75-2/Af
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+2 - 1.0E+4	ohms	ASTM D257
Volume Resistivity	1.0E+2 - 1.0E+4	ohms·cm	ASTM D257
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

