

KumhoSunny PC 3601

Polycarbonate

Shanghai KumhoSunny Plastics Co., Ltd.

Message:

3601 is a light diffusion resin. It offers good light diffusion and UV stability.

General Information			
Features	Good UV Resistance		
	High Light Transmission		
Uses	Automotive Applications		
	Electrical Parts		
	Electrical/Electronic Applications		
	LEDs		
	Lighting Applications		
UL File Number	E254819		
	E65424		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	5.0 to 15	g/10 min	ASTM D1238
Molding Shrinkage			
Flow	0.50 to 0.70	%	ASTM D955
--	0.50 to 0.70	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
--	62.0	MPa	ASTM D638
--	65.0	MPa	ISO 527-2/50
Tensile Elongation (Break)	110	%	ASTM D638
Flexural Modulus			
--	2250	MPa	ASTM D790
-- ¹	2300	MPa	ISO 178
Flexural Strength			
--	95.0	MPa	ASTM D790
-- ²	75.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ³			ISO 179

-30°C	15	kJ/m ²	
23°C	60	kJ/m ²	
Charpy Unnotched Impact Strength ⁴ (23°C)	No Break		ISO 179
Notched Izod Impact			
3.20 mm	550	J/m	ASTM D256
23°C ⁵	55	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed	130	°C	ASTM D648
1.8 MPa, Unannealed ⁶	121	°C	ISO 75-2/A
Vicat Softening Temperature	140	°C	ISO 306/B50
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-2		UL 94
Optical	Nominal Value	Unit	Test Method
Transmittance	80.0	%	ASTM D1003
Haze	98	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	100 to 120	°C	
Drying Time	4.0 to 6.0	hr	
Suggested Max Moisture	< 0.020	%	
Rear Temperature	240 to 270	°C	
Middle Temperature	250 to 290	°C	
Front Temperature	265 to 310	°C	
Nozzle Temperature	260 to 310	°C	
Processing (Melt) Temp	265 to 310	°C	
Mold Temperature	80.0 to 110	°C	
Back Pressure	0.200 to 0.800	MPa	
Screw Speed	20 to 100	rpm	
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		
3.	4J		
4.	4J		
5.	5.5J		
6.	120°C/h		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT