OTECH PVC OW633 - Cord Insulation

Polyvinyl Chloride

OTECH Corporation

Message:

FLEXIBLE CORD INSULATION COMPOUNDS Applications UL T, TW

In	isulating material
In	

Physical	Nominal Value	Unit
Specific Gravity	1.36	g/cm³
Hardness	Nominal Value	Unit
Durometer Hardness (10 sec)	83	
Mechanical	Nominal Value	Unit
Tensile Strength	18.3	MPa
Tensile Elongation (Break)	300	%
Additional Information	Nominal Value	Unit
Limited Oxygen Index	24	%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

