

MAXTEL® 620-BK

Polypropylene Copolymer

MRC Polymers, Inc.

Message:

For Injection Molding. Excellent process ability with high flow and high impact. Further information and details are available upon request.

General Information			
Features	Copolymer		
	Good Processability		
	High Flow		
	High Impact Resistance		
Appearance	Black		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.898	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	25	g/10 min	ISO 1133
Ash Content	< 1.0	%	ISO 294
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	18.0	MPa	ISO 527-2
Tensile Strain (Break)	100	%	ISO 527-2
Flexural Modulus	665	MPa	ISO 178
Flexural Stress	17.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	43	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed, 3.20 mm	67.0	°C	ISO 75-2/B
1.8 MPa, Unannealed, 3.20 mm	43.0	°C	ISO 75-2/A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT