

POLYFORT® FPP LGF 30

Polypropylene Homopolymer

A. Schulman Europe

Message:

30% long glass fiber reinforced PP Homopolymer

General Information			
Filler / Reinforcement	Long glass fiber, 30% filler by weight		
Features	Homopolymer		
Processing Method	Injection molding		
Resin ID (ISO 1043)	PP-H LGF 30		
Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	3.00	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7500	MPa	ISO 527-2/1A/1
Tensile Stress (Break)	110	MPa	ISO 527-2/1A/5
Tensile Strain (Break)	2.6	%	ISO 527-2/1A/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	18	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	60	kJ/m ²	ISO 179/1eU
Notched Izod Impact (23°C)	18	kJ/m ²	ISO 180/4A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	149	°C	ISO 75-2/Af
Flammability	Nominal Value	Unit	Test Method
Burning Rate (2.00 mm)	< 100	mm/min	ISO 3795
Flammability Classification (1.50 mm)	HB		IEC 60695-11-10, -20
Additional Information			

1.)

Not for use in food contact applications2.)

Not for use in medical or pharmaceutical applications

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

