

# Clearflex® RP 50 U

Linear Medium Density Polyethylene

Versalis S.p.A.

## Message:

Clearflex RP 50 U is a linear medium density polyethylene resin, with antioxidants and UV stabilizers, suitable for rotomoulding applications. Items manufactured with Clearflex RP 50 U show good mechanical properties and excellent surface aspect.

### Main Application

Thanks to high processability, Clearflex RP 50 U is recommended for the production of hardly shaped items with inner smooth surface, toys and bas-reliefs.

General Information			
Additive	Antioxidant		
	UV Stabilizer		
Features	Antioxidant		
	Food Contact Acceptable		
	Good Processability		
	Good Surface Finish		
	Good UV Resistance		
	Medium Density		
Uses	Toys		
Agency Ratings	EU Food Contact, Unspecified Rating		
Forms	Pellets		
Processing Method	Rotational Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.935	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	9.0	g/10 min	ISO 1133
Environmental Stress-Cracking Resistance (Injection Molded)	> 200	hr	ISO 22088
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, Injection Molded)	53		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2
Yield, Injection Molded	17.0	MPa	
Break, Injection Molded	16.0	MPa	
Tensile Strain (Break, Injection Molded)	> 700	%	ISO 527-2
Flexural Modulus (Injection Molded)	600	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Drop Impact Resistance (Rotomolded Specimen)	200	J/cm	ISO 6603-2

Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -70.0	°C	ASTM D746
Vicat Softening Temperature	113	°C	ISO 306/A
Melting Temperature	126	°C	Internal Method
Injection	Nominal Value	Unit	
Processing (Melt) Temp	230 to 280	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

