

TRIEX® Compound HF3000HG30

Polycarbonate
Samyang Corporation

Message:

TRIEX® Compound HF3000HG30 is a Polycarbonate (PC) product. It is available in Asia Pacific, Europe, or North America.

General Information			
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.34	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	8.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.30 to 0.50	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.11	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	122		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	103	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	6280	MPa	ASTM D790
Flexural Strength (Yield)	153	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	160	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	136	°C	ASTM D648
CLTE - Flow	1.9E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	4.0E+16	ohms·cm	ASTM D257
Dielectric Strength	31	kV/mm	ASTM D149
Dielectric Constant	3.29		ASTM D150
Dissipation Factor	9.7E-3		ASTM D150
Arc Resistance	120	sec	ASTM D495

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

