

Toyolac® 930-355

Methyl Methacrylate / ABS

Toray Resin Company

Message:

Toyolac® 930-355 is a Methyl Methacrylate / ABS (MABS) product. It is available in Asia Pacific, Europe, or North America.

Characteristics include:

Flame Rated

Impact Resistant

General Information			
Features	High Impact Resistance		
Appearance	Clear/Transparent		
Part Marking Code	>MABS<		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.08	g/cm ³	ASTM D792
23°C	1.08	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	23	g/10 min	ISO 1133
Molding Shrinkage	0.40 to 0.60	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C)	102		ASTM D785, ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
--	40.0	MPa	ASTM D638
23°C	45.0	MPa	ISO 527-2
Tensile Elongation			
Break	40	%	ASTM D638
Break, 23°C	16	%	ISO 527-2
Flexural Modulus			
--	1810	MPa	ASTM D790
23°C	1830	MPa	ISO 178
Flexural Strength			
--	61.0	MPa	ASTM D790
23°C	64.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	13	kJ/m ²	ISO 179
Notched Izod Impact			ASTM D256
23°C, 3.20 mm	190	J/m	
23°C, 12.7 mm	150	J/m	
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load			
1.8 MPa, Unannealed, 6.40 mm	80.0	°C	ASTM D648
1.8 MPa, Unannealed	74.0	°C	ISO 75-2/A
Vicat Softening Temperature	85.0	°C	
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Optical	Nominal Value	Unit	Test Method
Transmittance (Total, 3000 μm)	85.0	%	ISO 13468
Haze (3000 μm)	3.0	%	ISO 14782

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

