

DAI-EL™ G-7200BP

Fluoroelastomer

DAIKIN AMERICA, INC.

Message:

DAI-EL G-7200BP is a bisphenol curable, gum copolymer with low Mooney viscosity. It is designed especially for injection molding of seals and other complex shapes.

General Information			
Features	Copolymer		
Uses	Gaskets		
	Seals		
	Tubing		
Appearance	Brown		
	White		
Forms	Slab		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	
Specific Gravity	1.81	g/cm ³	
Mooney Viscosity (ML 1+10, 121°C)	24	MU	
Fluorine Content	66	%	
Low Temperature Brittleness - TR10	-18	°C	ASTM D1329
Hardness	Nominal Value	Unit	
Durometer Hardness ¹ (Shore A)	78		
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			
100% Strain, 25°C ²	5.40	MPa	
100% Strain, 25°C ³	5.50	MPa	
Tensile Strength			
Yield, 25°C ⁴	11.3	MPa	
Yield, 25°C ⁵	11.8	MPa	
Tensile Elongation			
Break, 25°C ⁶	190	%	
Break, 25°C ⁷	210	%	
Compression Set			ASTM D395B
200°C, 70 hr ⁸	18	%	
200°C, 70 hr ⁹	19	%	
NOTE			
1.	ODR, Strain: 3°, Test time: 12 min		

2.	ODR, Strain: 3°, Test time: 12 min
3.	MDR 2000, Strain: 0.5°, Test time: 6 min
4.	ODR, Strain: 3°, Test time: 12 min
5.	MDR 2000, Strain: 0.5°, Test time: 6 min
6.	ODR, Strain: 3°, Test time: 12 min
7.	MDR 2000, Strain: 0.5°, Test time: 6 min
8.	MDR 2000, Strain: 0.5°, Test time: 6 min
9.	ODR, Strain: 3°, Test time: 12 min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

