

NYLOY® MS-0100B-SP

Polyamide 66

Nytex Composites Co., Ltd.

Message:

NYLOY® MS-0100B-SP is a polyamide 66 (nylon 66) material. This product is available in North America or Asia Pacific region. The processing method is injection molding.

General Information			
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.06	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	39.2	MPa	ASTM D638
Tensile Elongation (Break)	60	%	ASTM D638
Flexural Modulus	1420	MPa	ASTM D790
Flexural Strength	58.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-29°C, 3.18 mm	690	J/m	ASTM D256
23°C, 3.18 mm	990	J/m	ASTM D256
Injection	Nominal Value	Unit	
Drying Temperature	110	°C	
Drying Time	1.0	hr	
Rear Temperature	270	°C	
Middle Temperature	280	°C	
Nozzle Temperature	290	°C	
Mold Temperature	80	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT