

POCAN® B 1505 000000

Polybutylene Terephthalate

LANXESS GmbH

Message:

PBT, non-reinforced, injection molding, extrusion

General Information			
UL YellowCard	E245249-100603183		
Agency Ratings	EC 1907/2006 (REACH)		
Processing Method	Extrusion		
	Injection molding		

Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.31	g/cm ³	ISO 1183
Apparent Density	0.80	g/cm ³	ISO 60
Melt Volume-Flow Rate (MVR) (250°C/2.16 kg)	16.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 2577
Vertical flow direction: 250°C, 2.00mm ¹	2.1	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 2.00mm ²	0.20	%	ISO 2577
Flow direction: 250°C, 2.00mm ³	2.1	%	ISO 2577
Flow direction: 120°C, 4 hours, 2.00mm ⁴	0.20	%	ISO 2577
Water Absorption			ISO 62
Saturated, 23°C	0.50	%	ISO 62
Equilibrium, 23°C, 50% RH	0.20	%	ISO 62

Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	120	MPa	ISO 2039-1

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
23°C	2470	MPa	ASTM D638
23°C	2700	MPa	ISO 527-2/1
Tensile Stress			
Yield, 23°C	60.0	MPa	ISO 527-2/50
Fracture, 23°C	33.8	MPa	ASTM D638
Tensile Strain			
Yield, 23°C	9.0	%	ISO 527-2/50
Fracture, 23°C	29	%	ASTM D638
Nominal Tensile Strain at Break (23°C)	> 15	%	ISO 527-2/50
Tensile Creep Modulus			
1 hr	2200	MPa	ISO 899-1

1000 hr	1300	MPa	ISO 899-1
Flexural Modulus			
23°C	2090	MPa	ASTM D790
23°C ⁵	2650	MPa	ISO 178/A
Flexural Strength			
23°C	85.5	MPa	ASTM D790
3.5% strain, 23°C	80.0	MPa	ISO 178/A
23°C ⁶	90.0	MPa	ISO 178/A
Flexural Strain at Flexural Strength (23°C) ⁷	6.0	%	ISO 178/A
Halving Interval			IEC 60216
Electric Strength	12.6	°C	IEC 60216
Tensile Impact Strength	12.0	°C	IEC 60216
Tensile Strength	12.6	°C	IEC 60216
Temperature index			IEC 60216
Electric Strength, 20000 hr	150	°C	IEC 60216
Tensile Impact Strength, 20000 hr	135	°C	IEC 60216
Tensile Strength, 20000 hr	150	°C	IEC 60216
Burning Behavior ⁸	passed		ISO 3795
Electrolytical Corrosion (23°C)	A 1		IEC 60426
ISO Shortname	PBT, GHMR, 11-030		ISO 7792
Residual Moisture Content	0.0 - 0.020	%	Karl Fisher
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	< 10	kJ/m ²	ISO 179/1eA
23°C	< 10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	180	kJ/m ²	ISO 179/1eU
23°C	No Break		ISO 179/1eU
Notched Izod Impact			ISO 180/1A
-40°C	< 10	kJ/m ²	ISO 180/1A
-30°C	< 10	kJ/m ²	ISO 180/1A
23°C	< 10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	150	kJ/m ²	ISO 180/1U
23°C	No Break		ISO 180/1U
Multi-Axial Instrumented Impact Energy			ISO 6603-2
-30°C	32.0	J	ISO 6603-2
23°C	22.0	J	ISO 6603-2
Multi-Axial Instrumented Impact Peak Force			ISO 6603-2
-30°C	5190	N	ISO 6603-2
23°C	3650	N	ISO 6603-2

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	150	°C	ISO 75-2/B
1.8 MPa, not annealed	60.0	°C	ISO 75-2/A
8.0 MPa, not annealed	45.0	°C	ISO 75-2/C
Ball Pressure Test (190°C)	Pass		IEC 60695-10-2
Melting Temperature ⁹	225	°C	ISO 11357-3
Linear thermal expansion coefficient			ISO 11359-2
Flow: 23 to 55°C	1.2E-4	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	1.2E-4	cm/cm/°C	ISO 11359-2
Thermal Conductivity (23°C)	0.25	W/m/K	ISO 8302
RTI Elec	140	°C	UL 746
RTI Imp	125	°C	UL 746
RTI	140	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength (23°C, 1.00 mm)	30	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
23°C, 100 Hz	3.40		IEC 60250
23°C, 1 MHz	3.20		IEC 60250
Comparative Tracking Index (Solution A)	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	HB		UL 94
1.60 mm	HB		UL 94
Glow Wire Flammability Index (2.00 mm)	750	°C	IEC 60695-2-12
Oxygen Index ¹⁰	24	%	ISO 4589-2
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Circulation Dryer	120	°C	
Drying Time - Circulation Dryer	4.0 - 8.0	hr	
Processing (Melt) Temp	250 - 260	°C	
Mold Temperature	80.0 - 100	°C	
NOTE			
1.	60x60x2mm, 80°C MT, 600 bar		
2.	60x60x2mm		
3.	60x60x2mm, 80°C MT, 600 bar		
4.	60x60x2mm		
5.	2.0 mm/min		
6.	2.0 mm/min		
7.	2 mm/min		
8.	US-FMVSS302		
9.	10°C/min		
10.	Procedure A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

