

OP - PC/ABS 604-I

Polycarbonate + ABS

Oxford Polymers

Message:

OP-PC/ABS 604-I is a polycarbonate acrylonitrile butadiene styrene (PC ABS) material. This product is available in North America and is processed by injection molding. The main characteristics of OP-PC/ABS 604-I are: flame retardant/rated flame.

General Information			
Features	General		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	8.5	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 - 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	52.4	MPa	ASTM D638
Fracture	53.8	MPa	ASTM D638
Flexural Modulus	2210	MPa	ASTM D790
Flexural Strength	72.4	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (4°C)	480	J/m	ASTM D256
Dart Drop Impact	36.2	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	113	°C	ASTM D648
1.8 MPa, not annealed	98.9	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.59 mm	HB		UL 94
3.18 mm	HB		UL 94
Additional Information			
Melt Mass -Flow Rate (MFR), ASTM D1238, 285°C/ 2.16kg: 3 to 14 g/10 min			
Injection	Nominal Value	Unit	
Drying Temperature	76.7 - 82.2	°C	
Drying Time	3.0 - 4.0	hr	
Drying Time, Maximum	8.0	hr	
Rear Temperature	249 - 288	°C	
Middle Temperature	254 - 293	°C	

Front Temperature	260 - 302	°C
Processing (Melt) Temp	274 - 302	°C
Mold Temperature	71.1 - 93.3	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

