

RTP 285 H HEC UV

Polyamide 66

RTP Company

Message:

Nickel-Coated Carbon Fiber - Electrically Conductive - EMI/RFI/ESD Protection - UV Stabilized

General Information			
Filler / Reinforcement	Nickel-plated carbon fiber, 30% filler by weight		
Additive	Impact modifier		
	UV stabilizer		
Features	Impact modification		
	Conductivity		
	Electromagnetic shielding (EMI)		
	Electrostatic discharge protection		
	Radio frequency shielding (RFI)		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.23	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.050 - 0.15	%	ASTM D955
Moisture Content	0.20	%	
Primary Additive	30	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	13800	MPa	ASTM D638
Tensile Strength	138	MPa	ASTM D638
Tensile Elongation (Yield)	3.0	%	ASTM D638
Flexural Modulus	12400	MPa	ASTM D790
Flexural Strength	234	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	110	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	640	J/m	ASTM D4812
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity			
--	< 1.0E+4	ohms	ASTM D257
--	< 1.0E+3	ohms	ESD STM11.11
Volume Resistivity	< 1.0	ohms · cm	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	

Drying Time	4.0	hr
Dew Point	-17.8	°C
Processing (Melt) Temp	277 - 299	°C
Mold Temperature	65.6 - 107	°C
Injection Pressure	68.9 - 124	MPa

Injection instructions

Remove hopper magnets.Desiccant Type Dryer Required.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

