

Wellamid® MRGF3822-BK

Polyamide 66

Wellman Engineering Resins

Message:

Wellamid® MRGF3822-BK is a Polyamide 66 (Nylon 66) material filled with 38% glass\mineral. It is available in Asia Pacific, Europe, Latin America, or North America for injection molding.

Typical application of Wellamid® MRGF3822-BK: Automotive

General Information			
Filler / Reinforcement	Glass\Mineral,38% Filler by Weight		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.46	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow : 23°C	0.80 to 1.2	%	
Flow : 23°C	0.70 to 1.1	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	100	MPa	ISO 527-2
Tensile Strain (Yield, 23°C)	3.0	%	ISO 527-2
Flexural Modulus (23°C)	6400	MPa	ISO 178
Flexural Stress (23°C)	160	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	4.0	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	205	°C	ISO 75-2/A
Melting Temperature (DSC)	260	°C	ISO 3146
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	293 to 310	°C	
Middle Temperature	282 to 293	°C	
Front Temperature	271 to 282	°C	
Nozzle Temperature	266 to 293	°C	
Processing (Melt) Temp	282 to 293	°C	
Mold Temperature	71.1 to 93.3	°C	
Injection Pressure	34.5 to 138	MPa	
Back Pressure	0.345	MPa	
Screw Speed	30 to 120	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

