

INSULCAST® 116 FR

Epoxy; Epoxide
ITW Polymers Coatings North America

Message:

INSULCAST 116 FR is a one to one ratio (weight or volume) epoxy potting and casting compound designed for production use. The convenient mixing ratio of the material makes it ideal for production line mixing as well as automatic dispensing. INSULCAST 116 FR is among the safest epoxy compounds available. It appreciably reduces the risk of eye, skin or respiratory problems generally associated with the use of epoxy compounds.

General Information			
UL YellowCard	E86165-251990		
Features	Flame Retardant		
UL File Number	E86165		
Processing Method	Casting		
	Potting		
Hardness	Nominal Value		Test Method
Durometer Hardness (Shore D)	75		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	65.5	MPa	ASTM D638
Tensile Elongation (Break)	8.0	%	ASTM D638
Flexural Strength	68.9	MPa	ASTM D790
Compressive Strength	86.2	MPa	ASTM D695
Thermal	Nominal Value	Unit	
CLTE - Flow	3.0E-5	cm/cm/°C	
Thermal Conductivity	0.43	W/m/K	
Heat Deflection Temperature	70	°C	
Service Temperature	105	°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms · cm	ASTM D257
Dielectric Strength	17	kV/mm	ASTM D149
Dielectric Constant (1 kHz)	4.40		ASTM D150
Dissipation Factor (1 kHz)	0.020		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
Mix Ratio by Volume: 1.0			
Part A	Mix Ratio by Weight: 1.0		

Mix Ratio by Volume: 1.0

Part B	Mix Ratio by Weight: 1.0		
Shelf Life (25°C)	52	wk	
Uncured Properties	Nominal Value	Unit	Test Method
Color			
-- 1	Black		
-- 2	Grey		
Density			
-- 3	1.45	g/cm ³	
-- 4	1.50	g/cm ³	
Viscosity			
-- 5	7.2	Pa·s	ASTM D2393
-- 6	8.1	Pa·s	
-- 7	11	Pa·s	ASTM D2393
Curing Time (22°C)	16 to 24	hr	
Gel Time (25°C)	1.8E+2 to 2.4E+2	min	
Pot Life ⁸	90	min	

NOTE

- | | |
|----|---------------|
| 1. | Part A |
| 2. | Part B |
| 3. | Part B |
| 4. | Part A |
| 5. | Part A |
| 6. | Mixed |
| 7. | Part B |
| 8. | 100 gram mass |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT