

Durethan® BKV 40 H3.0 000000

Polyamide 6

LANXESS Corporation

Message:

PA 6, 40 % glass fibers, injection molding, heat-aging stabilized

General Information				
Filler / Reinforcement	Glass fiber reinforced material, 40% filler by weight			
Additive	heat stabilizer			
Features	Thermal Stability			
Agency Ratings	EC 1907/2006 (REACH)			
Processing Method	Injection molding			
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.46	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 2577
Vertical flow direction: 280°C, 3.00mm ¹	0.85	--	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 3.00mm ²	0.070	--	%	ISO 2577
Flow direction: 280°C, 3.00mm ³	0.16	--	%	ISO 2577
Flow direction: 120°C, 4 hours, 3.00mm ⁴	0.030	--	%	ISO 2577
Water Absorption				ISO 62
Saturated, 23°C	6.0	--	%	ISO 62
Equilibrium, 23°C, 50% RH	1.8	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	12300	7800	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	205	130	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.0	5.0	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	11000	7300	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% strain, 23°C	--	180	MPa	ISO 178/A
23°C ⁶	325	205	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	4.0	5.0	%	ISO 178/A
ISO Shortname	PA 6, MHR, 14-120, GF40	--		ISO 1874
Residual Moisture Content	0.030 - 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA

-30°C	13	11	kJ/m ²	ISO 179/1eA
23°C	18	24	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	75	75	kJ/m ²	ISO 179/1eU
23°C	90	95	kJ/m ²	ISO 179/1eU
Notched Izod Impact				ISO 180/1A
-30°C	13	11	kJ/m ²	ISO 180/1A
23°C	18	24	kJ/m ²	ISO 180/1A
Multi-Axial Instrumented Impact Energy				ISO 6603-2
-30°C	6.00	--	J	ISO 6603-2
23°C	9.00	--	J	ISO 6603-2
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	215	--	°C	ISO 75-2/B
1.8 MPa, not annealed	200	--	°C	ISO 75-2/A
Vicat Softening Temperature	> 200	--	°C	ISO 306/B120
Melting Temperature ⁸	222	--	°C	ISO 11357-3
Linear thermal expansion coefficient				ISO 11359-2
Flow: 23 to 55°C	2.0E-5	--	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	8.0E-5	--	cm/cm/°C	ISO 11359-2
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+14	1.0E+12	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+15	1.0E+12	ohms · cm	IEC 60093
Dielectric Strength (23°C, 1.00 mm)	40	35	kV/mm	IEC 60243-1
Relative Permittivity				IEC 60250
23°C, 100 Hz	4.00	15.0		IEC 60250
23°C, 1 MHz	4.00	5.00		IEC 60250
Dissipation Factor				IEC 60250
23°C, 100 Hz	7.0E-3	0.20		IEC 60250
23°C, 1 MHz	0.015	0.12		IEC 60250
Comparative Tracking Index (Solution A)	525	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
1.60 mm	HB	--		UL 94
3.20 mm	HB	--		UL 94
Glow Wire Flammability Index (2.00 mm)	650	--	°C	IEC 60695-2-12
Oxygen Index ⁹	24	--	%	ISO 4589-2

Injection	Dry	Unit	Test Method
Drying Temperature - Dry Air Dryer	80.0		°C
Drying Time - Dry Air Dryer	2.0 - 6.0		hr
Processing (Melt) Temp	270 - 290		°C
Mold Temperature	80.0 - 120		°C

NOTE

- | | |
|----|-------------------------------|
| 1. | 150x105x3mm, 80°C MT, 400 bar |
| 2. | 150x105x3mm |
| 3. | 150x105x3mm, 80°C MT, 400 bar |
| 4. | 150x105x3mm |
| 5. | 2.0 mm/min |
| 6. | 2.0 mm/min |
| 7. | 2 mm/min |
| 8. | 10°C/min |
| 9. | Procedure A |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT