

Reslen PPH 30T

Polypropylene Homopolymer
Polimarky Spolka Jawna

Message:

Reslen PPH 30T is a Polypropylene Homopolymer (PP Homopolymer) product. It is available in Europe. Primary characteristic: homopolymer.

General Information			
Features	Homopolymer		
Physical	Nominal Value	Unit	Test Method
Density	1.14 to 1.16	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.0 to 20	g/10 min	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1900 to 2300	MPa	ISO 527-2
Tensile Stress	23.0 to 28.0	MPa	ISO 527-2
Tensile Strain (Break)	15 to 100	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	3.0 to 5.5	kJ/m ²	ISO 179/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	68.0	°C	ISO 75-2/A
Vicat Softening Temperature	157	°C	ISO 306/A120
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 120	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	220 to 260	°C	
Mold Temperature	40.0 to 70.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT