

Staramide AG6ST01

Polyamide 66

Eurostar Engineering Plastics

Message:

Staramide AG6ST01 is a is an Impact Modified, Glass Fiber Reinforced Polyamide 66 Injection Molding Resin

General Information			
Filler / Reinforcement	Glass Fiber		
Additive	Impact Modifier		
Features	Impact Modified		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.36	g/cm ³	ISO 1183
Molding Shrinkage - Flow ¹	0.20 to 0.40	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7400	MPa	ISO 527-2/1
Tensile Stress (Break)	130	MPa	ISO 527-2/5
Tensile Strain (Break)	4.0	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ²			ISO 180/1A
-20°C	8.0	kJ/m ²	
23°C	12	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ³			
0.45 MPa, Unannealed, 100 mm Span	245	°C	ISO 75-2/Be
1.8 MPa, Unannealed, 100 mm Span	235	°C	ISO 75-2/Ae
Vicat Softening Temperature	250	°C	ISO 306/B120
CLTE			ISO 11359-2
Flow : 23 to 60°C	2.7E-5	cm/cm/°C	
Transverse : 23 to 60°C	7.8E-5	cm/cm/°C	
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm, Tested by E2P)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	75.0 to 85.0	°C	
Drying Time	4.0 to 6.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	260 to 280	°C	
Middle Temperature	270 to 280	°C	
Front Temperature	270 to 290	°C	

Processing (Melt) Temp	270 to 290	°C
Mold Temperature	60.0 to 90.0	°C

NOTE		
1.	Tensile Bar	
2.	80*10*4	
3.	120*10*4	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT