

MAZMID C 350

Polyamide 6

Mazzaferro Indústria e Comércio de Polímeros e Fibras Ltda.

Message:

MAZMID C 350 is a Polyamide 6 (Nylon 6) product. It can be processed by coextrusion or extrusion and is available in Latin America. Typical application: Film.

Characteristics include:

Clarity

Good Tear Strength

General Information	
Features	Gas Barrier
	Good Tear Strength
	High Clarity
Uses	Film
Processing Method	Coextrusion
	Extrusion

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.12 to 1.14	g/cm ³	ASTM D792
Apparent Density	0.65	g/cm ³	ASTM D1895
Melt Mass-Flow Rate (MFR) (235°C/2.16 kg)	6.0 to 9.5	g/10 min	ASTM D1238
Viscosity Number	170 to 188	cm ³ /g	ISO 307
Ash Content	None		
Moisture Content	< 600	ppm	
Relative Viscosity - H2SO4	3.00 to 3.25		
Monomers	< 0.60	%	
Thermal	Nominal Value	Unit	
Melting Temperature	205 to 210	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT