

NHU-PPS 10100F

Polyphenylene Sulfide
Zhejiang NHU Comp. Ltd.

Message:

High temperature resistance, innoxious, flame resistance, radiation resistance, solvent resistance, electrical insulation properties. As a coating material, it can be used to spray on metal without a primer. The usage of PPS together with fluoroplastics enables PPS to have non—stick and abrasion resistance.

Applications

It can be used to make coating material which can be used as inner/outer coating of guideway, containers, metal mold, food pots, reaction kettles, storing tanks, storing cisterns, pipes and electric components.

General Information			
Features	Insulation		
	Anti-gamma radiation		
	Solvent resistance		
	Heat resistance, high		
	Flame retardancy		
Uses	Pipeline coating		
	Coating application		
Processing Method	Electrostatic jet coating		
	Sprayable		
	Coating		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (316°C/5.0 kg)	1700	g/10 min	ISO 1133
Ash Content (750°C)	0.4	wt%	ISO 3451
Weight Loss on Heating ¹	0.10	%	
Volatiles ²	0.45	%	
NOTE			
1.	150°C, 1 hour		
2.	300°C, 1 hour		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

