GAPEX® HPP40GR37HB NATURAL

Polypropylene Homopolymer

Ferro Corporation

Message:

GAPEX® HPP40GR37HB NATURAL is a polypropylene homopolymer (PP Homopoly) material, which contains 40% glass \minerals. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. GAPEX® The main characteristics of HPP40GR37HB NATURAL are: chemical coupling.

General Information			
Filler / Reinforcement	Glass \mineral, 40% filler by weight		
Features	Chemical coupling		
Appearance	Natural color		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.23	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.10	5		
kg)	8.0	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow	0.30	%	ASTM D955
Transverse flow	0.90	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	70.3	МРа	ASTM D638
Tensile Elongation (Break, 23°C)	3.0	%	ASTM D638
Flexural Modulus			ASTM D790
1% secant: 23°C	6240	MPa	ASTM D790
Tangent: 23°C	6800	MPa	ASTM D790
Flexural Strength (23°C)	103	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	69	J/m	ASTM D256
Unnotched Izod Impact (23°C)	380	J/m	ASTM D4812
Dart Drop Impact (23°C)	0.452	J	ASTM D5420
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	157	°C	ASTM D648
1.8 MPa, not annealed	143	°C	ASTM D648
Additional Information			

Testing and measurements were performed at 73 \pm -3°F and 50 \pm -5% relative humidity unless otherwise noted.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

