

Durethan® DP 2801 000000

Polyamide 66

LANXESS Corporation

Message:

PA 66, non-reinforced, injection molding, halogen free flame retardant

General Information				
UL YellowCard		E245249-473612		
Additive		Flame retardancy		
Features		Halogen-free		
		Flame retardancy		
Agency Ratings		EC 1907/2006 (REACH)		
Processing Method		Injection molding		
Resin ID (ISO 1043)		PA FR (30)		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.14	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 2577
Vertical flow direction: 280°C, 2.00mm ¹	1.2	--	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 2.00mm ²	0.11	--	%	ISO 2577
Flow direction: 280°C, 2.00mm ³	1.1	--	%	ISO 2577
Flow direction: 120°C, 4 hours, 2.00mm ⁴	0.42	--	%	ISO 2577
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	151	70.0	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	3500	1400	MPa	ISO 527-2/1
Tensile Stress				
Yield, 23°C	94.0	55.0	MPa	ISO 527-2/50
Fracture, 23°C	80.0	55.0	MPa	ISO 527-2/5
Tensile Strain				
Yield, 23°C	4.2	20	%	ISO 527-2/50
Fracture, 23°C	11	230	%	ISO 527-2/5
Nominal Tensile Strain at Break (23°C)	10	160	%	ISO 527-2/50
Flexural Modulus ⁵ (23°C)	3200	1300	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% strain, 23°C	105	36.0	MPa	ISO 178/A
23°C ⁶	127	49.0	MPa	ISO 178/A

Flexural Strain at Flexural Strength ⁷ (23°C)	6.2	8.0	%	ISO 178/A
Burning Behavior ⁸ (> 1.00 mm)	passed	--		ISO 3795
ISO Shortname	PA 66, GFHR, 14-030	--		ISO 1874
Admissible Residence Time at Tmax			min	
Residual Moisture Content	0.030 - 0.070		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	< 10	< 10	kJ/m ²	ISO 179/1eA
23°C	< 10	15	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	120	190	kJ/m ²	ISO 179/1eU
23°C	110 kJ/m ²	No Break		ISO 179/1eU
Notched Izod Impact				ISO 180/1A
-30°C	< 10	< 10	kJ/m ²	ISO 180/1A
23°C	< 10	10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	110	130	kJ/m ²	ISO 180/1U
23°C	80 kJ/m ²	No Break		ISO 180/1U
Multi-Axial Instrumented Impact Energy				ISO 6603-2
-30°C	5.10	--	J	ISO 6603-2
23°C	13.1	27.2	J	ISO 6603-2
Multi-Axial Instrumented Impact Peak Force				ISO 6603-2
-30°C	2400	--	N	ISO 6603-2
23°C	3730	4630	N	ISO 6603-2
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	210	--	°C	ISO 75-2/B
1.8 MPa, not annealed	75.0	--	°C	ISO 75-2/A
8.0 MPa, not annealed	60.0	--	°C	ISO 75-2/C
Vicat Softening Temperature	> 230	--	°C	ISO 306/B120
Ball Pressure Test (249°C)	Pass	--		IEC 60695-10-2
Melting Temperature ⁹	265	--	°C	ISO 11357-3
Linear thermal expansion coefficient				ISO 11359-2
Flow: 23 to 55°C	7.0E-5	--	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	9.0E-5	--	cm/cm/°C	ISO 11359-2

Electrical	Dry	Conditioned	Unit	Test Method
Comparative Tracking Index				IEC 60112
Solution a	600	--	V	IEC 60112
Solution B ¹⁰	400	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.750 mm)	V-2	--		UL 94
Glow Wire Flammability Index (1.00 mm)	960	--	°C	IEC 60695-2-12
Glow Wire Ignition Temperature				IEC 60695-2-13
0.750 mm	775	--	°C	IEC 60695-2-13
1.50 mm	775	--	°C	IEC 60695-2-13
3.00 mm	775	--	°C	IEC 60695-2-13
Oxygen Index ¹¹	30	--	%	ISO 4589-2
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 - 6.0		hr	
Processing (Melt) Temp	260 - 270		°C	
Mold Temperature	80.0 - 100		°C	

NOTE

- 60x60x2mm, 80°C MT, 600 bar
- 60x60x2mm
- 60x60x2mm, 80°C MT, 600 bar
- 60x60x2mm
- 2.0 mm/min
- 2.0 mm/min
- 2 mm/min
- US-FMVSS302
- 10°C/min
- Erosion depth: 1.80mm
- Procedure A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

