

EVALENE® PP PHJ0501

Polypropylene Homopolymer

JG Summit Petrochemical Corporation

Message:

PP is used in making films, adhesive tapes, cigarette and candy wrappers, cosmetics, pharmaceutical and food packaging materials.

High Clarity. Hot-Fill Applications. Living Hinge.

Evalene® Random Copolymer PP is widely used in the following applications:

Injection Molding: Houseware, lunch boxes and pencil cases with "living hinges"

Blow Molding: Baby bottles, bottles for juice, tea, water, medicine, and cosmetics

Good Economics. Hot-Fill Applications. Excellent Film Clarity. Good Tenacities.

Evalene® Homopolymer PP is the material of choice for a host of applications:

Tape Extrusion: Woven bags for rice, cement and industrial chemicals

Films: Bi-axially oriented, cast and inflation films for tapes, packaging, and labels

Injection Molding: Monobloc furnitures, pails, houseware, containers, toys, caps

Thermoforming: Fastfood containers, mineral water cups

General Information			
Features	Fast Molding Cycle		
	Good Toughness		
	Homopolymer		
Uses	Furniture		
	Pails		
Agency Ratings	FDA Unspecified Rating		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	5.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, Injection Molded)	100		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus - 1% Secant ¹ (Injection Molded)	1590	MPa	ASTM D638
Tensile Strength ² (Yield, Injection Molded)	38.0	MPa	ASTM D638
Tensile Elongation ³ (Yield, Injection Molded)	20	%	ASTM D638
Flexural Modulus - 1% Secant ⁴ (Injection Molded)	1670	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, Injection Molded)	30	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (0.45 MPa, Unannealed, Injection Molded)	102	°C	ASTM D648
Peak Melting Temperature ⁵	163	°C	ASTM D3418
Injection	Nominal Value	Unit	
Processing (Melt) Temp	200 to 220	°C	
Mold Temperature	20.0 to 40.0	°C	
NOTE			
1.	5.0 mm/min		
2.	50 mm/min		
3.	50 mm/min		
4.	1.3 mm/min		
5.	10°C/min, 2nd heating		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

