

INVISION™ TX 5173U

Thermoplastic Vulcanizate

A. Schulman Inc.

Message:

TPV Fully Crosslinked EPDM Rubber

General Information			
Processing Method	Blow Molding		
	Coextrusion		
	Profile Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.970	g/cm ³	ISO 1183/A
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A, 15 sec, 23°C)	74		ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ¹ (Break, 23°C)	7.00	MPa	ISO 37
Tensile Elongation ² (Break, 23°C)	350	%	ISO 37
Tear Strength ³ (23°C)	25	kN/m	ISO 34-1
NOTE			
1.	Type 1, 500 mm/min		
2.	Type 1, 500 mm/min		
3.	Method Ba, Angle (Unnicked), 500 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT