

Karina IVORY PVC COMPOUND 951-35/4-IS

Polyvinyl Chloride

Karina Ind. e Com. de Plásticos Ltda

Message:

FLAME RETARDANT PVC COMPOUND WITH HIGH ELECTRICAL INSULATION RESISTANCE RECOMMENDED FOR INSULATION OF CI AND CCI CABLES.

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
Uses	Electronic Insulation		
	Wire & Cable Applications		
Appearance	Ivory		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	1.30 to 1.34	g/cm ³	ASTM D792
Color	0.00OK		ME 12
Color a	-0.880 to 2.12		ME 12
Color b	5.58 to 8.58		ME 12
Color L	85.0 to 88.0		ME 12
Maximum Variation of Elongation	< 40	%	NBR 9148
Maximum Variation of Tensile Strength	< 20	%	NBR 9148
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 15 sec	92 to 96		
Shore D	61 to 65		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	> 12.6	MPa	NBR 9141
Tensile Elongation (Yield)	> 130	%	NBR 9141
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength ²	> 12.6	MPa	NBR 9148
Tensile Elongation ³ (Break)	> 130	%	NBR 9148
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity ⁴	> 6.0E+14	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	> 23	%	NBR 6245
NOTE			
1.	24 hr		
2.	Aged in Air for 168 hr at 100°C		
3.	Aged in Air for 168 hr at 100°C		
4.	24 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

