

Larpeek 10 G/60

Polyetheretherketone

LATI S.p.A.

Message:

Compound based on Polyetheretherketone (PEEK).
UL94 V-0 classified, halogens free. Glass fibres.
Very good chemical resistance. Very good thermal resistance. Low smoke toxicity index and optical density.

General Information			
Filler / Reinforcement	Glass Fiber,60% Filler by Weight		
Features	Good Chemical Resistance		
	Halogen Free		
	High Heat Resistance		
Physical	Nominal Value	Unit	Test Method
Density	1.82	g/cm ³	ISO 1183
Molding Shrinkage ¹			ISO 294-4
Across Flow : 2.00 mm	0.30 to 0.55	%	
Flow : 2.00 mm	0.15 to 0.35	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			ISO 527-2/1
23°C	23000	MPa	
60°C	22500	MPa	
90°C	22500	MPa	
120°C	22000	MPa	
150°C	21500	MPa	
Tensile Stress			ISO 527-2/5
Break, 23°C	225	MPa	
Break, 60°C	215	MPa	
Break, 90°C	200	MPa	
Break, 120°C	180	MPa	
Break, 150°C	160	MPa	
Tensile Strain			ISO 527-2/5
Break, 23°C	1.7	%	
Break, 60°C	1.7	%	
Break, 90°C	1.7	%	
Break, 120°C	1.7	%	
Break, 150°C	1.8	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	50	kJ/m ²	ISO 179/1eU

Notched Izod Impact (23°C, 3.20 mm)	95	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	> 300	°C	ISO 75-2/B
1.8 MPa, Unannealed	> 300	°C	ISO 75-2/A
Continuous Use Temperature ²	240	°C	
Vicat Softening Temperature	> 300	°C	ISO 306/B50
CLTE - Flow (30 to 100°C)	6.0E-6	cm/cm/°C	ASTM D696
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.750 mm	V-1		
1.50 mm	V-0		
3.00 mm	V-0		
Glow Wire Flammability Index (2.00 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (1.00 mm)	875	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	120 to 150	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	370 to 400	°C	
Mold Temperature	170 to 200	°C	
Injection Rate	Fast		
NOTE			
1.	at 60 Mpa of cavity pressure		
2.	20,000 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

