

# Okirol® E-6

Expanded Polystyrene

DIOKI d.d.

## Message:

Okirol® E-6 is expandable polystyrene containing pentane as the blowing agent. The product is supplied as spherical beads.

Okirol® E-6 is used for the manufacture of medium and high density blocks, panels and shapes for general and specific purposes and thin walled moulded parts

General Information			
Additive	Blowing Agent		
Uses	Reinforced Panels		
	Thin-walled Parts		
Agency Ratings	EC 1907/2006 (REACH)		
	EU 2002/72/EC		
	EU 94/62/EC		
RoHS Compliance	RoHS Compliant		
Forms	Spheres		
Physical	Nominal Value	Unit	Test Method
Density			
-- <sup>1</sup>	0.0190	g/cm <sup>3</sup>	
-- <sup>2</sup>	0.0200 to 0.0300	g/cm <sup>3</sup>	EN 1602
Apparent Density	0.62	g/cm <sup>3</sup>	ISO 60
Additional Information	Nominal Value	Unit	Test Method
Bead Size			ISO 2591-1
--	500.0 to 700.0	µm	
Range <sup>3</sup>	400.0 to 800.0	µm	
Blowing Agent	5.0 to 6.5	%	ASTM 7132-05
NOTE			
1.	Minimum density of expanded beads		
2.	Density of molded product		
3.	>95%		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

