

DIC.PPS FZ-1130-D5

Polyphenylene Sulfide

DIC Corporation

Message:

Outline: FZ-1130-D5 is a glass fiber 30% reinforced polyphenylene sulfide compound with reduced flash and improved flexibility compared to conventional grades.
Color: Black and Natural (Brown).

General Information			
UL YellowCard	E53829-243754		
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Good Flexibility		
UL File Number	E53829		
Appearance	Black		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.56	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.27	%	
Across Flow	1.2	%	
Water Absorption (23°C, 24 hr)	0.020	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	100		
R-Scale	121		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	11000	MPa	ASTM D638
Tensile Strength	175	MPa	ASTM D638
Tensile Elongation (Break)	1.9	%	ASTM D638
Flexural Modulus	10000	MPa	ASTM D790
Flexural Strength	240	MPa	ASTM D790
Compressive Strength	190	MPa	ASTM D695
Poisson's Ratio	0.36		
Coefficient of Friction ¹			ASTM D1894
vs. Steel - Dynamic	0.35		
vs. Steel - Static	0.35		
Flexural Elongation at Break	2.5	%	ASTM D790

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	95	J/m	ASTM D256
Unnotched Izod Impact	550	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	265	°C	ASTM D648
CLTE			ASTM D696
Flow : -30 to 90°C	2.3E-5	cm/cm/°C	
Transverse : -30 to 90°C	2.3E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength (1.60 mm)	16	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	4.00		ASTM D150
Dissipation Factor (1 MHz)	2.0E-3		ASTM D150
Arc Resistance	120	sec	ASTM D495
Comparative Tracking Index	170	V	ASTM D3638
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.800 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Rear Temperature	300 to 340	°C	
Middle Temperature	300 to 340	°C	
Front Temperature	300 to 340	°C	
Mold Temperature	120 to 150	°C	
NOTE			
1.	P=150KPa, V=0.3m/s		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

