

Durethan® DP 1441/40 H2.0 EF 900116

Polyamide 6

LANXESS Corporation

Message:

PA 6, 40 % glass fibers/mineral, injection molding, improved flowability, heat-aging stabilized, low tendency to warp, improved surface finish

General Information				
Filler / Reinforcement		Glass\Mineral,40% Filler by Weight		
Additive		Heat Stabilizer		
Features		Good Flow		
		Good Surface Finish		
		Heat Stabilized		
		Low Warpage		
Agency Ratings		EC 1907/2006 (REACH)		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.45	--	g/cm ³	ISO 1183
Apparent Density	0.70	--	g/cm ³	ISO 60
Molding Shrinkage				ISO 2577
Across Flow : 290°C, 2.00 mm ¹	0.72	--	%	
Across Flow : 120°C, 4 hr, 2.00 mm ²	0.11	--	%	
Flow : 290°C, 2.00 mm ³	0.31	--	%	
Flow : 120°C, 4 hr, 2.00 mm ⁴	0.050	--	%	
Across Flow : 290°C, 3.00 mm ⁵	0.87	--	%	
Across Flow : 120°C, 4 hr, 3.00 mm ⁶	0.15	--	%	
Flow : 290°C, 3.00 mm ⁷	0.25	--	%	
Flow : 120°C, 4 hr, 3.00 mm ⁸	0.050	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	210	95.0	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	9000	4500	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	125	65.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	2.5	8.7	%	ISO 527-2/5
Flexural Modulus ⁹ (23°C)	8800	4250	MPa	ISO 178/A
Flexural Stress				ISO 178/A

3.5% Strain,23°C	200	110	MPa	
23°C ¹⁰	206	125	MPa	
Flexural Strain at Flexural Strength ¹¹ (23°C)	2.9	6.2	%	ISO 178/A
ISO Shortname	ISO 1874 PA 6, GHR, 10-080, (GF+MD) 40			ISO 1874
Residual Moisture Content	0.030 to 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	< 10	--	kJ/m ²	
23°C	< 10	< 10	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	37	45	kJ/m ²	
23°C	40	65	kJ/m ²	
Notched Izod Impact Strength				ISO 180/1A
-30°C	< 10	--	kJ/m ²	
23°C	< 10	10	kJ/m ²	
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	33	30	kJ/m ²	
23°C	35	60	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	215	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	195	--	°C	ISO 75-2/A
Melting Temperature ¹²	220	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C	2.8E-5	--	cm/cm/°C	
Transverse : 23 to 55°C	8.5E-5	--	cm/cm/°C	
Flammability	Dry	Conditioned		Test Method
Flame Rating				UL 94
0.800 mm	HB	--		
1.60 mm	HB	--		
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 to 6.0		hr	
Processing (Melt) Temp	280 to 300		°C	
Mold Temperature	80.0 to 100		°C	
NOTE				
1.	60x60x2mm, 80°C MT, 600 bar			

2.	60x60x2mm
3.	60x60x2mm, 80°C MT, 600 bar
4.	60x60x2mm
5.	150x105x3mm, 80°C MT, 500 bar
6.	150x105x3mm
7.	150x105x3mm, 80°C MT, 500 bar
8.	150x105x3mm
9.	2.0 mm/min
10.	2.0 mm/min
11.	2 mm/min
12.	10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT