

TUFNYL® SGF 30 FR0 HF NATURAL

Polyamide 6

SRF Ltd.

Message:

Polyamide 6, 30% Glass fiber reinforced, flame retardant, halogen free material for injection molding

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Flame Retardant		
	Halogen Free		
Appearance	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.15 to 0.35	%	Internal Method
Water Absorption (Equilibrium)	0.80	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness	ASTM D785		
M-Scale	81		
R-Scale	115		
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	90.0	MPa	ISO 527-2
Tensile Strain (Break)	2.5	%	ISO 527-2
Flexural Modulus	7500	MPa	ISO 178
Flexural Stress	145	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	49.0	J/m	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	> 200	°C	ISO 75-2/B
1.8 MPa, Unannealed	> 200	°C	ISO 75-2/A
Melting Temperature	220	°C	DSC
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	ASTM D257
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257
Dielectric Strength	18	kV/mm	ASTM D149
Comparative Tracking Index	> 400	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94

Injection	Nominal Value	Unit
Drying Temperature	80.0	°C
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	< 0.20	%
Processing (Melt) Temp	280 to 300	°C
Mold Temperature	40.0 to 80.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

