

Lapex R G/10

Polyphenylsulfone

LATI S.p.A.

Message:

Compound based on Polyphenylensulphone (PPSU).

UL94 V-0 classified, halogens free. Glass fibres.

Low smoke density and low toxicity index. Very high dimensional stability.

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Features	Good Dimensional Stability		
	Halogen Free		
Physical	Nominal Value	Unit	Test Method
Density	1.37	g/cm ³	ISO 1183
Molding Shrinkage ¹			ISO 294-4
Across Flow : 2.00 mm	0.85 to 1.0	%	
Flow : 2.00 mm	0.45 to 0.60	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			ISO 527-2/1
23°C	4000	MPa	
60°C	3850	MPa	
90°C	3700	MPa	
120°C	3550	MPa	
150°C	3400	MPa	
Tensile Stress			ISO 527-2/5
Break, 23°C	105	MPa	
Break, 60°C	100	MPa	
Break, 90°C	90.0	MPa	
Break, 120°C	80.0	MPa	
Break, 150°C	70.0	MPa	
Tensile Strain			ISO 527-2/5
Break, 23°C	2.8	%	
Break, 60°C	2.6	%	
Break, 90°C	2.6	%	
Break, 120°C	2.5	%	
Break, 150°C	2.3	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	20	kJ/m ²	ISO 179/1eU
Notched Izod Impact (23°C, 3.20 mm)	90	J/m	ASTM D256A

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	220	°C	ISO 75-2/B
1.8 MPa, Unannealed	210	°C	ISO 75-2/A
Continuous Use Temperature ²	190	°C	
Vicat Softening Temperature	220	°C	ISO 306/B50
CLTE - Flow (30 to 100°C)	1.5E-5	cm/cm/°C	ASTM D696
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm	V-0		
3.00 mm	V-0		
Oxygen Index	38	%	ASTM D2863
Injection	Nominal Value	Unit	
Drying Temperature	140 to 180	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	350 to 390	°C	
Mold Temperature	150 to 190	°C	
Injection Rate	Fast		
NOTE			
1.	at 60 Mpa of cavity pressure		
2.	20,000 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT