ELASTOSIL® LR 3003/20 TR A/B

Silicone

Wacker Chemie AG

Message:

Silicone Rubber, LSR
Molded Parts, Food Contact, Plastics and Rubber Processing
Molded Parts, Technical, Plastics and Rubber Processing
Molded Parts, Automotive, Plastics and Rubber Processing
Molded Seals, Plastics and Rubber Processing

Vibration Dampers, Automotive & Transportation

General Information	
Features	Food Contact Acceptable
	General Purpose
Uses	Automotive Applications
	Automotive Under the Hood
	Gaskets
	Membranes
	Seals
	Valves/Valve Parts
Processing Method	Injection Molding

Liquid Injection Molding (LIM)

Uncured Properties	Nominal Value	Unit	Test Method
Color	Clear/Transparent		
Density	1.08	g/cm³	ISO 1183
Viscosity	180	Pa∙s	DIN 53019
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	20		DIN 53505
Tensile Strength	8.00	MPa	DIN 53504
Tensile Elongation at Break	860	%	DIN 53504
Compression Set	18	%	DIN ISO 815-B
Tear Strength	26.0	kN/m	ASTM D624B
Rebound Resilience	45	%	DIN 53512
Electric Strength	23	kV/mm	DIN IEC 243
Volume Resistivity	5.0E+15	ohms·cm	DIN IEC 93
Dissipation Factor (50 Hz)	2.0E-4		DIN VDE 0303

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

