

GLS ABS SN06

Acrylonitrile Butadiene Styrene

GLS Polymers Pvt. Ltd.

Message:

ABS FR V0

General Information			
Features	Flame Retardant		
Appearance	Colors Available		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.17	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	> 20	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.40 to 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	> 44.0	MPa	ASTM D638
Tensile Elongation ² (Yield)	> 8.0	%	ASTM D638
Flexural Modulus ³	> 1800	MPa	ASTM D790
Flexural Strength ⁴	> 50.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	> 80	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	> 82.0	°C	ASTM D648
Vicat Softening Temperature	> 96.0	°C	ASTM D1525 ⁵
Flammability	Nominal Value	Test Method	
Flame Rating (3.00 mm)	V-0	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	206 to 236	°C	
Mold Temperature	65.0 to 86.0	°C	
Injection Pressure	70.0 to 101	MPa	
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	2.0 mm/min		
4.	2.0 mm/min		
5.	Rate B (120°C/h)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

