

HOPELEX PC-1220S

Polycarbonate

Lotte Chemical Corporation

Message:

Low viscosity, No mold release agent and no UV Stabilizer
Compounds

General Information			
UL YellowCard	E85371-100144914		
Features	Low Viscosity		
Uses	Compounding		
RoHS Compliance	RoHS Compliant		
Processing Method	Compounding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	22	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	61.8	MPa	ASTM D638
Tensile Elongation ² (Break)	> 100	%	ASTM D638
Flexural Modulus ³	2350	MPa	ASTM D790
Flexural Strength ⁴ (Yield)	90.2	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	690	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	139	°C	
1.8 MPa, Unannealed	128	°C	
Vicat Softening Temperature	150	°C	ASTM D1525 ⁵
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.585		ASTM D542
Transmittance	89.0	%	ASTM D1003
Haze	< 0.80	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Suggested Max Regrind	20	%	
Hopper Temperature	60.0 to 80.0	°C	
Rear Temperature	290 to 310	°C	

Middle Temperature	280 to 300	°C
Front Temperature	270 to 290	°C
Nozzle Temperature	280 to 300	°C
Processing (Melt) Temp	290 to 310	°C
Mold Temperature	60.0 to 90.0	°C

NOTE		
1.	50 mm/min	
2.	50 mm/min	
3.	10 mm/min	
4.	10 mm/min	
5.	Rate B (120°C/h), Loading 2 (50 N)	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT